


Product Data Sheet

Tung Oil



Product	Pure Tung Oil (Chinawood Oil)
Size	1L
Description	Tung oil is transparent or slightly turbid liquid, extracted from the seeds of tung tree.
Used For	Widely used in production of alkyd resin, raw lacquer, varnish and paint. Ideal for timber treatments where water repellency is required.
Surface Preparation	<p>Ensure the surface is clean and dry before application. Gilly's Citrus Thin (d-limonene, natural citrus solvent) or a turpentine can be used for a vigorous clean. For a lighter clean, you can use an all purpose cleaner.</p> <p>If there is any oil, wax, grease, dirt or similar residue on the surface, it may affect the tung oil's ability to cure - so a thorough clean is important.</p>
How to Apply To Raw Timber	<ol style="list-style-type: none">1. Blend with Gilly's Citrus Thin at a ratio of 50/50.2. Rub or brush oil into the timber. Lighter coats are better.3. Let it sit for 5 minutes. Wipe on more oil to areas that become dull, as the oil soaks in.4. Wipe off the excess oil, then lightly sand back whilst still damp. Use 320 grit or finer.5. Apply 3 coats, repeating the same procedure. Best to wait 24 hours between coats. Apply more coats if desired or necessary.6. Hang out any rags or soak in water.
Dry Time	24 hours to dry between coats. As this is tung oil based, it can take 4 weeks to completely cure. Light usage is however perfectly fine within this time frame..
Maintenance	For general maintenance and wear, you can assess as you see fit. We would recommend reapplying a light 1-2 coats every 6-12 months to keep your timber looking fresh.
Clean Up	D-Limonene or mineral turpentine. Warm, soapy water for hand washing.

<p>Safety</p>	<ul style="list-style-type: none"> • Do not eat, drink or smoke around product. Wash hands after use. • Hang out rags to dry, or soak in water. Don't leave scrunched up. • Contact Gilly's for SDS
<p>Ingredients</p>	<p>Tung oil 100%</p>
<p>Image</p>	

W: www.gillysaustralia.com.au
E: orders@gillysaustralia.com.au
Ph: (08) 9295 1973